

**TECHNICAL DATA**

**POLYESTER C200 G2 ROUND + GLASS FIBRE + VARNISH**

**High Temperature Enamel & Textile Insulated Copper Wire**

**DESCRIPTION**

POLYESTER C200 G2 consists of a round copper conductor with a dual coat enamel of polyesterimide or THEIC modified polyester base coat with a polyamide-imide overcoat according to IEC 60317-13.  
POLYESTER C200 G2 enamelled wire is then insulated with a single or double covering of glass fibre followed by impregnation with a choice of high temperature resins.  
Impregnation is available with epoxy (V155), polyesterimide (V180) and silicone (V200) resin systems.  
B-stage thermally adhesive varnishes can also be used for thermal classes 155 and 180°C. (V155K & V180K).

**APPLICATIONS**

POLYESTER C200 G2 + GLASS FIBRE wires provide high mechanical and bond strength, along with good resistance to abrasion and solvents.  
POLYESTER C200 G2 + GLASS FIBRE wires find use in rotating machines up to 6kV, as well as windings which are subject to constantly high thermal and mechanical stress, such as magnet coils.

**BUILD CRITERIA**

Bare Conductor Diameter	Total insulation increase - Polyester C200 Grade 2 + Glass Fibre			
	Single Layer		Double Layer	
	Fine Build	Reinforced Build	Fine Build	Reinforced Build
0.80 - 1.40mm	0.13 - 0.18mm	0.15 - 0.20mm	0.20 - 0.25mm	0.30 - 0.35mm
1.40mm - 2.00mm	0.19 - 0.23mm	0.24 - 0.27mm	0.26 - 0.31mm	0.31 - 0.36mm
2.00mm +	0.19 - 0.23mm	0.24 - 0.27mm	0.30 - 0.36mm	0.34 - 0.40mm

\* Insulation increase and tolerances of Polyester C200 Grade 2 Enamelled wires according to IEC 60317-0-1.

**PROPERTIES**

**POLYESTER C200 GRADE 2 ENAMELLED WIRE**

Temperature class, IEC 600851-6	200°C
Enamel - Base coat	Polyesterimide or Polyester (THEIC)
Enamel - Top coat	Polyamide-imide
Size range able to be covered with Glass Fibre	0.800 - 6.000mm
Grades	Grade 2

**POLYESTER C200 GRADE 2 + GLASS FIBRE**

**THERMAL PROPERTIES**

Thermal index, NEMA MW 1000	
Polyester C200 G2 + 1 or 2 Glass Fibre + V155/V155K	155°C
Polyester C200 G2 + 1 or 2 Glass Fibre + V180/V180K	180°C
Polyester C200 G2 + 1 or 2 Glass Fibre + V200	200°C
Heat shock, 30 mins @ 180°C 10 x d, IEC 60851-6 Test 9	
Polyester C200 G2 + 1 or 2 Glass Fibre + V155/V155K	No cracks
Heat shock, 30 mins @ 200°C 10 x d, IEC 60851-6 Test 9	
Polyester C200 G2 + 1 or 2 Glass Fibre + V180/V180K	No cracks
Polyester C200 G2 + 1 or 2 Glass Fibre + V200	No cracks

® Registered trademark

Statements, technical information and recommendations contained herein are based on tests we believe to be reliable but they are not to be construed in any manner as warranties expressed or implied. The user shall determine the suitability of the product for their intended use and the user assumes all risk and liability whatsoever in connection therewith.

**POLYESTER C200 G2 ROUND + GLASS FIBRE + VARNISH**

**MECHANICAL PROPERTIES (ALL TYPES)**

Springiness, Dia. $\geq$ 1.60mm, IEC 60851-3 Test 7	$\leq$ 5.5
Flexibility - Mandrel winding 10 x d, IEC 60851-3 Test 8	No cracks
Adhesion after 10% elongation, IEC 60851-3 Test 8	No loss of adhesion
Shear strength, V155K & V180K, FIM test no. 1.47.14	$\geq$ 3 N/mm <sup>2</sup>

**ELECTRICAL PROPERTIES**

Breakdown voltage after bending, IEC 60851-5 Test 13	
Polyester C200 G2 + 1 Glass Fibre	$\geq$ 2,750V
Polyester C200 G2 + 2 Glass Fibre	$\geq$ 3,000V

**STANDARDS**

Polyester C200 G2 Enamelled Wire	IEC 60317-13 NEMA/ANSI type MW 35C UL Approved, Class 200
Polyester C200 G2 + 1 or 2 Glass Fibre + V155	IEC 60317-48
Polyester C200 G2 + 1 or 2 Glass Fibre + V180	IEC 60317-49
Polyester C200 G2 + 1 or 2 Glass Fibre + V200	IEC 60317-50
Dimensions & Tolerances	IEC 60317-0-6
Methods of test	IEC 60851
Packaging	IEC 60264

**SHELF-LIFE**

Polyester C200 G2 + 1 or 2 Glass Fibre	Indefinite
Polyester C200 G2 + 1 or 2 Glass Fibre + V155	Indefinite
Polyester C200 G2 + 1 or 2 Glass Fibre + V180	Indefinite
Polyester C200 G2 + 1 or 2 Glass Fibre + V200	Indefinite
Polyester C200 G2 + 1 or 2 Glass Fibre + V155K	12 months @ 25°C & 60% relative humidity
Polyester C200 G2 + 1 or 2 Glass Fibre + V180K	12 months @ 25°C & 60% relative humidity

**LEGISLATION**

RoHS compliant	Yes
REACH SVHC concentration	0%