

Foxwood Close Foxwood Industrial Park Sheepbridge Chesterfield Derbyshire S41 9RB United Kingdom T: 01246 261 828 F: 01246 261 830 sales@par.gb.com www.par.gb.com

nqa. ISO 9001 Registered 015

Page 1 of 1

TECHNICAL DATA

VIDASCRIM[®] - Woven Glass Tape

DESCRIPTION

Woven tape constructed from a plain weave of 'E' glass yarns which have been treated with Amino Silane. The Amino Silane treatment allows good adhesion of varnishes and resins. Vidascrim® tapes are renowned for their resistance to chemicals and good 'wet out' characteristics.

APPLICATIONS

Vidascrim® tapes are ideal where it is necessary to promote a high degree of bond between impregnating varnishes and resins, the tape yarns and other substrates.

Because of these properties, Vidascrim[®] is widely used for the repair, jointing and joint reinforcement in a range of fibreglass built products, such as boats and racing cars.

PHYSICAL PROPERTIES

Weave	Scrim
Standard thickness	0.17mm ± 0.025mm
Area weight	172g/m ²
Standard widths	25, 40, 50, 75, 100, 150mm (Others on request)
Tolerance on width ≤ 75mm	± 1.0mm
Tolerance on width >75mm	± 2.0mm
Temperature classification, IEC 60085	220°C (Class C)
Maximum short-term temperature	500°C
Standard roll length	50 metres (Others on request)
Standard centres	38mm cardboard (Others on request)

HEALTH & SAFETY

Before use, please refer to Material Safety Data Sheets (MSDS).

Registered trademark

Statements, technical information and recommendations contained herein are based on tests we believe to be reliable but they are not to be construed in any manner as warranties expressed or implied. The user shall determine the suitability of the product for their intended use and the user assumes all risk and liability whatsoever in connection therewith.