

Foxwood Close
Foxwood Industrial Park
Sheepbridge
Chesterfield
Derbyshire
S41 9RB
United Kingdom

T: 01246 261 828 F: 01246 261 830 sales@par.uk.com www.par.uk.com

TECHNICAL DATA
DOLPH'S® MR-737
Red Masking Lacquer



Page 1 of 1

DESCRIPTION

MR-737 was specially developed to prevent the adhesion of Dolph's[®] varnishes to metal surfaces and electronic components during the impregnation process.

After the impregnation and curing process is complete, MR-737 is easily peeled away form the component surface.

ADVANTAGES

- ightarrow High temperature resistance does not crack in baking cycle
- → Remains elastic easily peeled off
- → Good adhesion to a variety of substrates
- → Non corrosive

PHYSICAL PROPERTIES	
Colour	Red
Specific gravity @ 25°C	970 ± 30g/L
Viscosity, Ford No8 Cup @ 25°C	60 - 80 seconds
Film thickness, 1 layer	0.15 - 0.20mm
Drying time for handling @ 25°C	5 minutes
Total drying time @ 25°C	20 minutes (Time will vary depending on thickness)
Resistance to mineral oil	Excellent
Thinner	T-25
Shelf life @ 25°C in original closed containers	36 months
Pack sizes	1 Litre

APPLICATION

- 1. Apply MR-737 on parts that must be protected from varnish via either a spatula, brush, or by dipping. Take care to avoid contamination of zones where varnish must adhere.
- 2. A thicker layer may be required to cover rough or concave surfaces, or where screw heads or holes are present.
- 3. Ensure the coat is thick enough to be able to peel off after impregnation without tearing. Avoid coats that are too thick or thin.
- 4. Allow to air-dry for around 20 minutes. Drying time will depend on film thickness.
- 5. Impregnate and cure the component as usual.
- 6. When the component has cooled, MR-737 is easily removed by scoring the film and peeling off.

HEALTH & SAFETY

Before use, please refer to Material Safety Data Sheets (MSDS).

® Registered trademark

Statements, technical information and recommendations contained herein are based on tests we believe to be reliable but they are not to be construed in any manner as warranties expressed or implied. The user shall determine the suitability of the product for their intended use and the user assumes all risk and liability whatsoever in connection therewith.